

FLOORCO

ENVIRO TECHNICAL DATA, ANTI-STATIC & ESD TILES

TECHNICAL DATA

Anti-Static Industrial

Technical Data	Standard	Enviro Industrial 5mm,
Tile Dimensions		5mm: 516mmx516mm (10 tiles per pack)
Weight		5mm: 7.6kg/m ²
Hardness	ISO868	92 ShoreA
Material		PVC SGI 1.45
Thickness	BS EN 428	5mm
Wear Resistance	BS EN 660-2	Wear Group T
Caster Wheel	BS EN 425	No Damage
Indentation	BS EN 433	0.06mm
Fire Class	EN 13501-1	Bfl-s1
Electrical Resistance	BS EN 1081	10 ⁸ - 10 ⁹
Anti Slip	BS EN 13893 Deutsche Norm DIN 51130	Anti Slip DS R10
Chemical Resistance	BS EN 423	Good
Light Fastness (Blue Wool Standard)	BS EN 20105 - B02	7BWS/5GSR
Thermal Conductivity	ISO 8302	0.03807m ² K/W
Electrostatic Behaviour	BS EN 1815	2kV
Flexibility	BS EN 435	Flexibility No Cracking
Dimensional Stability Before Exposure to Heat	BS EN 434	0.11%
Dimensional Stability After Exposure to Heat	BS EN 434	Average 0.19
Density	BS EN 436: 1994	Average 1404kg/m ²



UK Office:

Eastway Enterprise Centre,
7 Paynes Park,
Hitchin,
Herts., SG5 1EH
T. 01462757019

E-mail: info@premierfloorcompany.co.uk

Web: www.premierfloorcompany.co.uk

TECHNICAL DATA ANTI-STATIC & ESD

Technical Data	Standard	Enviro Industrial 5mm,
Tile Dimensions		5mm: 516mmx516mm (10 tiles per pack)
Weight		5mm: 7.6kg/m ²
Hardness	ISO868	92 ShoreA
Material		PVC SGI 1.45
Thickness	BS EN 428	5mm
Wear Resistance	BS EN 660-2	Wear Group T
Caster Wheel	BS EN 425	No Damage
Indentation	BS EN 433	0.06mm
Fire Class	EN 13501-1	Bfl-s1
Electrical Resistance	BS EN61340-5-1:2001	10 ⁴ - 10 ⁷
Anti Slip	BS EN 13893 Deutsche Norm DIN 51130	Anti Slip DS R10
Chemical Resistance	BS EN 423	Good
Light Fastness (Blue Wool Standard)	BS EN 20105 - B02	7BWS/5GSR
Thermal Conductivity	ISO 8302	0.03807m2K/W
Electrostatic Behaviour	BS EN 1815	2kV
Flexibility	BS EN 435	Flexibility No Cracking
Dimensional Stability Before Exposure to Heat	BS EN 434	0.11%
Dimensional Stability After Exposure to Heat	BS EN 434	Average 0.19
Density	BS EN 436: 1994	Average 1404kg/m ²